## Abstract Submitted to the International Conference on Strongly Correlated Electron Systems University of Michigan, Ann Arbor August 6-10, 2001

## Optical Transitions in Non-Stoichiometric LaMnO $_3$ Identifying Charge Transfer Transitions $^*$

N.N. Kovaleva<sup>1</sup>, J. Gavartin<sup>2</sup>, A.V. Boris<sup>1</sup>, and A. M. Stoneham<sup>2</sup>

- <sup>1</sup> Institute of Solid State Physics, Russian Academy of Sciences, Chernogolovka, Moscow distr., 142432, RUSSIA
- <sup>2</sup> University College London, Gower Street, London WC1E 6BT, UK

Self-trapping of charge carriers is always associated with photo-induced charge transfer (CT) transitions. Using the Mott-Littleton approach we calculate energies of the main CT transitions involving  $\mathrm{Mn^{4+}}$  and  $\mathrm{O^{-}}$  localized holes, which determine specific electronic transport properties of doped CMR materials of  $\mathrm{La_{(1-x)}A_{x}MnO_{3}}$  (where A - divalent alkaline-earth ions). In these calculations extensive use is made of results on in-crystal ionization potentials of  $\mathrm{Mn^{3+}}$  and  $\mathrm{O^{2-}}$  ions from a companion paper\*. Our Mott-Littleton calculations predict energies for the main optical bands, which match these observed in the experimental optical conductivity spectrum near 2.3, 5 and 9 eV in the LaMnO<sub>3</sub> crystal. Experimental low-energy optical conductivity bands well agree with our calculated CT transitions involving  $\mathrm{Mn^{4+}}$  and  $\mathrm{O^{-}}$  localized holes. The reasonable agreement with experiment of our predicted energies, linewidth and oscillatior strength leads us to plausible assignment of the optical bands observed.

\* N.N. Kovaleva, J. Gavartin, A. Shluger, A.V. Boris, and A. M. Stoneham, "Formation and Relaxation Energies of Electronic Holes in LaMnO<sub>3</sub> Crystal"

<sup>\*</sup>This work was supported by the Royal Society/NATO